

# Chemlon® 225 GH

Teknor Apex Company (Chem Polymer) - Polyamide 6

Tuesday, December 19, 2017

## General Information

### General

Material Status	• Commercial: Active		
Availability	• Asia Pacific	• Europe	• North America
Filler / Reinforcement	• Glass Fiber, 25% Filler by Weight		
Additive	• Heat Stabilizer	• Lubricant	
Features	• Good Dimensional Stability	• Heat Stabilized	
	• Good Impact Resistance	• Lubricated	
Appearance	• Black	• Natural Color	
Forms	• Pellets		
Processing Method	• Injection Molding		

## ASTM & ISO Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.35		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	21500	psi	ASTM D638
Tensile Elongation (Break)	2.5	%	ASTM D638
Flexural Modulus	930000	psi	ASTM D790
Flexural Strength	31500	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F)	2.0	ft-lb/in	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load 264 psi, Unannealed	410	°F	ASTM D648
Melting Temperature	420	°F	

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

Teknor Apex Company Corporate Headquarters	Teknor Apex U.K. Ltd.	Teknor Apex (Suzhou) Advanced Polymer Compounds Co. Pte. Ltd.	Teknor Apex Asia Pacific PTE. LTD.
<i>In U.S. for Vinyls, TPEs, Colorants, Engineered Thermoplastics (Chem Polymer)</i> 505 Central Avenue Pawtucket, Rhode Island 02861 U.S.  Phone: 401-725-8000 Fax: 401-725-8095 Toll Free (U.S. only) 800-556-3864  <a href="http://www.teknorapex.com">www.teknorapex.com</a> <a href="mailto:info@teknorapex.com">info@teknorapex.com</a>	Tat Bank Road Oldbury, West Midlands B69 4NH England  Phone: (44) 121-665-2100 Fax: (44) 121-544-5530  <a href="http://www.teknorapex.com">www.teknorapex.com</a> <a href="mailto:etpsales@teknorapex.co.uk">etpsales@teknorapex.co.uk</a>	No. 78 Ping Sheng Road Suzhou Industrial Park Jiangsu, China 215126  Phone: (86) 512-6287-1550 Fax: (86) 512-6288-8371  <a href="http://www.teknorapex.com">www.teknorapex.com</a> <a href="mailto:infotaap@teknorapex.com">infotaap@teknorapex.com</a>	41 Shipyard Road Singapore 628134  Phone: (65) 6265-2544 Fax: (65) 6265-1821  <a href="http://www.teknorapex.com">www.teknorapex.com</a> <a href="mailto:infotaap@teknorapex.com">infotaap@teknorapex.com</a>

Revision Date: 12/11/2008

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.