



Product Data Sheet

Eastar Copolyester EB062

Key Attributes

- Exceptional clarity
- Good impact strength
- Outstanding chemical resistance
- High gloss
- Toughness
- Excellent colorability
- Easy to extrude, cut, print, and seal
- Effective barrier properties
- Good stiffness

Product Description

Eastar Copolyester EB062 is a resin specifically developed for extrusion blown bottles where aesthetics such as high clarity and gloss, coupled with design flexibility, drive demand. Compared to commonly used materials, *Eastar* copolyester EB062 runs on most standard processing equipment. Extremely high melt strength makes the resin an excellent choice when manufacturing large bottles.

List of Applications

- Beverage packaging
- Bottles
- Extrusion blow molding
- Food packaging

Typical Properties

Property ^a	Test ^b Method	Typical Value, Units ^c
General Properties		
Density	D 792	1.25 g/cm ³
Mold Shrinkage	D 955	0.3%
Mechanical Properties		
Tensile Stress @ Yield	D 638	47 MPa (6900 psi)
Tensile Stress @ Break	D 638	48 MPa (7000 psi)
Elongation @ Yield	D 638	5%
Elongation @ Break	D 638	300%
Tensile Modulus	D 638	1900 MPa (2.7 x 10 ⁵ psi)
Flexural Modulus	D 790	1900 MPa (2.7 x 10 ⁵ psi)
Flexural Strength	D 790	65 MPa (9400 psi)
Rockwell Hardness, R Scale	D 785	105
Izod Impact Strength, Notched ^d		

@ 23°C (73°F)	D 256	NB
@ -40°C (-40°F)	D 256	63C J/m (1.2C ft·lbf/in.)
Impact Strength, Unnotched ^e		
@ 23°C (73°F)	D 4812	NB
@ -40°C (-40°F)	D 4812	NB
Impact Resistance (Puncture), Energy @ Max. Load		
@ 23°C (73°F)	D 3763	41 J (30 ft·lbf)
@ 0°C (32°F)	D 3763	41 J (30 ft·lbf)
@ -40°C (-40°F)	D 3763	39 J (29 ft·lbf)

Thermal Properties

Deflection Temperature		
@ 0.455 MPa (66 psi)	D 648	73°C (163°F)
@ 1.82 MPa (264 psi)	D 648	63°C (145°F)
Vicat Softening Temperature		
	D 1525	85°C (185°F)

Optical Properties

Haze	D 1003	1.3%
Gloss @ 60°	D 2457	143
Regular Transmittance	D 1003	87%
Total Transmittance	D 1003	91%
Color		
L*	D 2244	95.0
a*	D 2244	-0.2
b*	D 2244	0.6

^a Unless noted otherwise, all tests are run at 23°C (73°F) and 50% relative humidity.

^b Unless noted otherwise, the test method is ASTM.

^c Units are in SI or US customary units.

^d C = Complete Break; Nonbreak as defined by ASTM D 256.

^e Nonbreak as defined by ASTM D 4812.

Comments

Properties reported here are typical of average lots. Eastman makes no representation that the material in any particular shipment will conform exactly to the values given.

Eastman Chemical Company and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.

19-Nov-2003 6:41:38 AM