

# Lustran 633

Acrylonitrile Butadiene Styrene (ABS)

## TECHNICAL DATASHEET

### DESCRIPTION

Lustran® 633 is a general-purpose injection molding grade of ABS (Acrylonitrile Butadiene Styrene). It offers a good balance of physical properties, high gloss, and good moldability.

### FEATURES

- Good moldability
- High gloss
- High impact strength
- UL 94 HB Rated

### APPLICATIONS

- Consumer goods
- Toys
- Appliances and housings

Property, Test Condition	Standard	Unit	Values
<b>Rheological Properties</b>			
Melt Flow Rate, 230 °C/3.8 kg	ASTM D 1238	g/10 min	4.5
<b>Mechanical Properties</b>			
Izod Notched Impact Strength, 23°C (73°F)	ASTM D 256	ft-lb/in	6.5
Izod Notched Impact Strength, -40°C (-40°F)	ASTM D 256	ft-lb/in	1.2
Tensile Stress at Yield, 23° C	ASTM D 638	psi	10000
Tensile Modulus	ASTM D 638	psi x 10 <sup>3</sup>	325
Flexural Modulus	ASTM D 790	psi x 10 <sup>3</sup>	315
Flexural Stress at 5% Deflection	ASTM D 790	psi	95000
Hardness, Rockwell	ASTM D 785	R scale	109
<b>Thermal Properties</b>			
Vicat Softening Temperature, B/1 ( 120°C/h, 10N)	ASTM D 1525	°F	-
Coefficient of Linear Thermal Expansion	ASTM D 696	10 <sup>-4</sup> /°F	0.50
<b>Optical Properties</b>			
Specular Gloss, 60°	ASTM D 523	%	90
<b>Other Properties</b>			
Density	ASTM D 792	-	1.05

# Lustran 633

Acrylonitrile Butadiene Styrene (ABS)

## TECHNICAL DATASHEET

Property, Test Condition	Standard	Unit	Values
<b>Processing</b>			
Linear Mold Shrinkage	ASTM D 955	in/in	0.004 - 0.006
Drying Temperature		°F	175
Drying Time		h	2-4

Typical values for uncolored products

### SUPPLY FORM

Lustran® ABS (Acrylonitrile Butadiene Styrene) resins are available in bulk railcar, bulk truckload and 726kg box quantities.

### REGULATORY COMPLIANCE

Please refer to Styrolution web site or contact Styrolution Technical Service for further information.

### PROCESSING

A reciprocating screw injection molding machine is preferred. A general-purpose screw with a 2.5:1 compression ratio is suggested. A minimum L/D ratio of 20:1 will ensure melt homogeneity. For best part quality, use the lower range of the recommended melt temperature with minimum barrel residence time. To avoid excessive residence time in the barrel, volume and weight of the shot should be balanced against barrel capacity and injection stroke. A shot weight-to-machine capacity ratio of 0.5-0.75 is recommended. A mold temperature of 110°-150°F (45°-65°C) is recommended for development of maximum gloss and strength, with the hotter end of this range preferred.

### PRODUCT SAFETY

Safety Data Sheets and product labels provide information concerning the health and safety precautions that must be observed when handling the Styrolution products mentioned in this publication. No adverse effects on the health of processing personnel have been observed if the products are correctly processed and the production areas are suitably ventilated. For styrene, acrylonitrile, alpha-methyl styrene, maleic anhydride and 1, 3-butadiene, the maximum allowable workplace concentrations must be observed according to current local and federal regulations. Before working with any of these products, you must read and become familiar with the available information on their hazards, proper use, and handling. This cannot be overemphasized. This information is available in safety data sheets and on product labels. If there are questions or concerns, consult your Styrolution representative or contact the Product Safety and Regulatory Affairs Department at Styrolution.

**DISCLAIMER**

The above information is provided in good faith. INEOS Styrolution is not responsible for any processing or compounding which may occur to product finished articles, packaging materials or their components. Further, INEOS Styrolution MAKES NO WARRANTY OR REPRESENTATION OF ANY KIND, REGARDING THE INFORMATION GIVEN OR THE PRODUCTS DESCRIBED, AND EXPRESSLY DISCLAIMS ALL IMPLIED WARRANTIES, REPRESENTATIONS AND CONDITIONS, INCLUDING WITHOUT LIMITATION ALL WARRANTIES AND CONDITIONS OF QUALITY, MERCHANTABILITY AND SUITABILITY OR FITNESS FOR A PARTICULAR PURPOSE. Responsibility for use, storage, handling and disposal of the products described herein is that of the purchaser or end user.