

## LUSTRAN<sup>®</sup> SAN DN Grades

### *Mass SAN Grades for Use in Compounding*

Lustran SAN DN grades are natural color, styrene-acrylonitrile copolymers supplied in pellet form.

Typical Properties*	ASTM Test Method (Other)	Lustran <sup>®</sup> SAN DN50	Lustran <sup>®</sup> SAN DN52	Lustran <sup>®</sup> SAN DN59	Lustran <sup>®</sup> SAN DN77	Lustran <sup>®</sup> SAN DN79	Lustran <sup>®</sup> SAN 51
<b>General</b> Melt Flow Rate at 230°C/3.8-kg Load % Acrylonitrile	D 1238	12 g/10 min 23.2%	7.5 g/10 min 23.2%	25 g/10 min 29.5%	14 g/10 min 31.0%	7.5 g/10 min 31.0%	5.4 g/10 min 33%
<b>Mechanical</b> Tensile Stress at Fail Flexural Stress at Fail Flexural Modulus Izod Impact Unnotched	D 638 D 790 D 790 D 256	10,300 lb/in <sup>2</sup> 16,000 lb/in <sup>2</sup> 495,000 lb/in <sup>2</sup> 4.5 ft-lbs/in	10,500 lb/in <sup>2</sup> 16,700 lb/in <sup>2</sup> 500,000 lb/in <sup>2</sup> 3.8 ft-lbs/in	10,000 lb/in <sup>2</sup> 11,000 lb/in <sup>2</sup> 495,000 lb/in <sup>2</sup> 5.8 ft-lbs/in	10,000 lb/in <sup>2</sup> 11,000 lb/in <sup>2</sup> 500,000 lb/in <sup>2</sup> 6.0 ft-lbs/in	11,500 lb/in <sup>2</sup> 14,000 lb/in <sup>2</sup> 525,000 lb/in <sup>2</sup> 6.8 ft-lbs/in	11,000 lb/in <sup>2</sup> 13,500 lb/in <sup>2</sup> 520,000 lb/in <sup>2</sup> 7.0 ft-lbs/in
<b>Thermal</b> Vicat Softening Temperature 1-kg load, 120°C/hour	D 1525	110°C	110°C	109°C	109°C	111°C	110°C

\* These items are provided as general information only. They are approximate values and are not part of the product specifications.

Note: The information contained in this publication is current as of July 2014. Please contact INEOS ABS to determine whether this publication has been revised.

The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by us. Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale. All information and technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with patents covering any material or its use. No license is implied or in fact granted under the claims of any patent.

**INEOS**  
**ABS**

INEOS ABS (USA) Corporation  
INEOS ABS NAFTA  
356 Three Rivers Parkway  
Addyston, OH 45001

[www.ineos-abs.com](http://www.ineos-abs.com)