

# Sarlink® TPV 3150

Teknor Apex Company - Thermoplastic Vulcanizate

Friday, October 7, 2016

## General Information

### Product Description

SARLINK® TPV 3100 series are engineered materials designed primarily for general purpose, automotive and industrial applications requiring a good balance of thermal, mechanical, and physical properties. SARLINK® 3150, available in NAT and BLK, is a medium hardness, low density, multi-purpose thermoplastic vulcanizate that can be processed by injection molding, blow molding or extrusion for applications such as grips, seals, gaskets, profiles, hose & tubes, bellows, and other articles.

### General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Chemical Resistant • Good Adhesion • Good Flexibility • Good Moldability • Good Processability	• Good Surface Finish • High Elasticity • Low Density • Low Specific Gravity • Medium Hardness	• Medium Heat Resistance • Resilient • Weather Resistant
Uses	• Automotive Applications • Automotive Exterior Parts • Automotive Interior Parts • Automotive Under the Hood • Diaphragms	• Gaskets • General Purpose • Industrial Applications • O-rings • Profiles	• Rubber Replacement • Seals • Weatherstripping
Agency Ratings	• UL 94		
RoHS Compliance	• RoHS Compliant		
Automotive Specifications	• CHRYSLER MS-AR-80 Type A Color: Black • CHRYSLER MS-AR-80 Type A Color: Natural • GM QK 003513 Color: Black • GM QK 003513 Color: Natural	• HONDA Unspecified Color: Black • PSA Peugeot-Citroën SPA Color: Black • RENAULT F.R.M. 6A 05 A08 Color: Black • VAG VW501 23 Color: Black	• VAG VW501 79 Color: Black • VOLKSWAGEN VW 50180 Color: Black
Appearance	• Black	• Natural Color	• Opaque
Forms	• Pellets		
Processing Method	• Blow Molding	• Extrusion	• Injection Molding

## ASTM & ISO Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.948	g/cm <sup>3</sup>	ASTM D792
Density	0.950	g/cm <sup>3</sup>	ISO 1183
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412
Across Flow : 100% Strain	1.90	MPa	
Flow : 100% Strain	3.00	MPa	
Tensile Stress			ISO 37
Across Flow : 100% Strain	1.90	MPa	
Flow : 100% Strain	3.00	MPa	
Tensile Strength			ASTM D412
Across Flow : Break	5.10	MPa	
Flow : Break	4.10	MPa	
Tensile Stress			ISO 37
Across Flow : Break	5.10	MPa	
Flow : Break	4.10	MPa	

Revision Date: 6/1/2016

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

# Sarlink® TPV 3150

## Teknor Apex Company - Thermoplastic Vulcanizate

<b>Elastomers</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Tensile Elongation			ASTM D412
Across Flow : Break	600	%	
Flow : Break	240	%	
Tensile Elongation			ISO 37
Across Flow : Break	600	%	
Flow : Break	240	%	
Tear Strength - Across Flow	24.5	kN/m	ASTM D624
Tear Strength - Across Flow <sup>2</sup>	24	kN/m	ISO 34-1
Compression Set			ASTM D395
23°C, 22 hr	20	%	
70°C, 22 hr	32	%	
125°C, 70 hr	52	%	
Compression Set			ISO 815
23°C, 22 hr	20	%	
70°C, 22 hr	32	%	
125°C, 70 hr	52	%	
<b>Hardness</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Durometer Hardness			ASTM D2240
Shore A, 5 sec, Extruded	54		
Shore A, 5 sec, Injection Molded	56		
Shore Hardness			ISO 868
Shore A, 5 sec, Extruded	54		
Shore A, 5 sec, Injection Molded	56		
<b>Thermal</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
RTI Elec	50.0	°C	UL 746
RTI Imp	50.0	°C	UL 746
RTI Str	50.0	°C	UL 746
<b>Aging</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Change in Tensile Strength in Air - Across Flow			ASTM D573
135°C, 1000 hr	-6.0	%	
100% Strain, 135°C, 1000 hr	7.0	%	
150°C, 168 hr	7.0	%	
100% Strain, 150°C, 168 hr	5.0	%	
Change in Tensile Strength in Air - Across Flow			ISO 188
135°C, 1000 hr	-6.0	%	
100% Strain 135°C, 1000 hr	7.0	%	
150°C, 168 hr	7.0	%	
100% Strain 150°C, 168 hr	5.0	%	
Change in Ultimate Elongation in Air - Across Flow			ASTM D573
135°C, 1000 hr	-7.0	%	
150°C, 168 hr	8.0	%	
Change in Tensile Strain at Break in Air - Across Flow			ISO 188
135°C, 1000 hr	-7.0	%	
150°C, 168 hr	8.0	%	
Change in Durometer Hardness in Air			ASTM D573
Shore A, 135°C, 1000 hr	1.0		
Shore A, 150°C, 168 hr	2.0		

Revision Date: 6/1/2016

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

# Sarlink® TPV 3150

## Teknor Apex Company - Thermoplastic Vulcanizate

Aging	Nominal Value	Unit	Test Method
Change in Shore Hardness in Air			ISO 188
Shore A, 135°C, 1000 hr	1.0		
Shore A, 150°C, 168 hr	2.0		
Change in Volume (125°C, 70 hr, in IRM 903 Oil)	130	%	ASTM D471
Change in Volume (125°C, 70 hr, in IRM 903 Oil)	130	%	ISO 1817
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.5 mm, Natural and Black Colors)	HB		UL 94
Additional Information	Nominal Value	Unit	Test Method
Apparent Shear Viscosity - Capillary, @ 206/s			
200°C	270	Pa·s	ISO 11443
200°C	270	Pa·s	ASTM D3835

### Legal Statement

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchaser assumes all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or others. There is no warranty of merchantability and there are no other warranties for the products described. For detailed Product Stewardship information, please contact us. Any product of Teknor Apex, including product names, shall not be used or tested in medical or food contact applications without the prior written acknowledgement of Teknor Apex as to the intended use. Please note that some products may not be available in one or more countries.

### Processing Information

Injection	Nominal Value	Unit
Rear Temperature	180 to 215	°C
Middle Temperature	180 to 215	°C
Front Temperature	180 to 215	°C
Nozzle Temperature	187 to 220	°C
Processing (Melt) Temp	185 to 220	°C
Mold Temperature	10 to 55	°C
Back Pressure	0.100 to 1.00	MPa
Screw Speed	100 to 200	rpm
Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	180 to 200	°C
Cylinder Zone 2 Temp.	180 to 205	°C
Cylinder Zone 3 Temp.	187 to 210	°C
Cylinder Zone 4 Temp.	187 to 210	°C
Melt Temperature	195 to 215	°C
Die Temperature	195 to 215	°C
Take-Off Roll	20 to 50	°C

### Extrusion Notes

Screen Pack: 20 to 60 mesh  
Screw: general purpose  
Compression Ratio: 3:1

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> Method Ba, Angle (Unnicked)

Revision Date: 6/1/2016

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

# Sarlink® TPV 3150

## Teknor Apex Company - Thermoplastic Vulcanizate

### Teknor Apex Company Corporate Headquarters

*In U.S. for Vinyls, TPEs, Colorants,  
Engineered Thermoplastics (Chem Polymer)*  
505 Central Avenue  
Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000  
Fax: 401-725-8095  
Toll Free (U.S. only) 800-556-3864

[www.teknorapex.com](http://www.teknorapex.com)  
[info@teknorapex.com](mailto:info@teknorapex.com)

### Teknor Apex U.K. Ltd.

Tat Bank Road  
Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100  
Fax: (44) 121-544-5530

[www.teknorapex.com](http://www.teknorapex.com)  
[etpsales@teknorapex.co.uk](mailto:etpsales@teknorapex.co.uk)

### Teknor Apex (Suzhou) Advanced Polymer Compounds Co. Pte. Ltd.

No. 78 Ping Sheng Road  
Suzhou Industrial Park  
Jiangsu, China 215126

Phone: (86) 512-6287-1550  
Fax: (86) 512-6288-8371

[www.teknorapex.com](http://www.teknorapex.com)  
[infotaap@teknorapex.com](mailto:infotaap@teknorapex.com)

### Teknor Apex Asia Pacific PTE. LTD.

41 Shipyard Road  
Singapore 628134

Phone: (65) 6265-2544  
Fax: (65) 6265-1821

[www.teknorapex.com](http://www.teknorapex.com)  
[infotaap@teknorapex.com](mailto:infotaap@teknorapex.com)

Revision Date: 6/1/2016

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.