

Technical Datasheet

DESCRIPTION

Styrolux® 3G46 is a clear styrene-butadiene copolymer (SBC) developed specifically for sheet- and film extrusion and for thermoformed articles. Styrolux® 3G46 is designed for improved performance in blends with general-purpose polystyrene, providing parts with an excellent balance of transparency and toughness.

FEATURES

- Outstanding transparency
- Good toughness / stiffness balance
- High GPPS blend capability
- Regulatory compliant

APPLICATIONS

- Food and non-food packaging
- Caps and lids
- Toys
- Displays
- Medical devices

Property, Test Condition	Standard	Unit	Values
Rheological Properties			
Melt Volume Rate, 200 °C/5 kg	ISO 1133	cm ³ /10 min	12
Mechanical Properties			
Izod Notched Impact Strength, 23 °C	ISO 180/A	kJ/m ²	3
Izod Notched Impact Strength, -30 °C	ISO 180/A	kJ/m ²	2
Charpy Notched Impact Strength, 23° C	ISO 179	kJ/m ²	3
Charpy Unnotched, 23° C	ISO 179	kJ/m ²	No Break
Tensile Stress at Yield, 23° C	ISO 527	MPa	27
Tensile Strain at Yield, 23° C	ISO 527	%	2
Tensile Modulus	ISO 527	MPa	1550
Nominal Strain at Break, 23 °C	ISO 527	%	180
Elongation at Break (MD)	ISO 527	%	180
Flexural Strength	ISO 178	MPa	31
Flexural Modulus	ISO 178	MPa	1550
Flexural Stress at 5% Deflection		MPa	31
Hardness, Shore D	ISO 868	-	65
Thermal Properties			

Styrolux 3G46

Styrene Butadiene Copolymer (SBC)

INEOS
STYROLUTION

Property, Test Condition	Standard	Unit	Values
Vicat Softening Temperature VST/B/50 (50N, 50°C/h)	ISO 306	°C	51
Vicat Softening Temperature, VST/A/50 (10N, 50°C/h)	ISO 306	°C	81
Heat Deflection Temperature A; (annealed 4 h/80 °C; 1.8 MPa)	ISO 75	°C	58
Heat Deflection Temperature B; (annealed 4 h/80 °C; 0.45 MPa)	ISO 75	°C	75
Coefficient of Linear Thermal Expansion	ISO 11359	10 ⁻⁶ /°C	60 - 90
Electrical Properties			
Dielectric Constant (100 Hz)	IEC 60250	-	2.5
Dissipation Factor (100 Hz)	IEC 60250	10 ⁻⁴	3
Dissipation Factor (1 MHz)	IEC 60250	10 ⁻⁴	8
Volume Resistivity	IEC 60093	Ohm*m	>1E13
Surface Resistivity	IEC 60093	Ohm	1E15
Comparative Tracking Index	IEC 60112	V	600
Optical Properties			
Refractive Index, Sodium D Line	ISO 489	-	1.573
Light Transmission at 550 nm	ASTM D 1003	%	90
Haze	ASTM D 1003	%	1
Other Properties			
Density	ISO 1183	kg/m ³	1020
Water Absorption, Saturated at 23°C	ISO 62	%	0.07
Processing			
Linear Mold Shrinkage	ISO 294-4	%	0.3 - 1
Melt Temperature Range	ISO 294	°C	180 to 250
Mold Temperature Range	ISO 294	°C	30 to 50

Typical values for uncolored products

SUPPLY FORM

Styrolux is supplied in pellet form and should be kept in its original containers in cool, dry place. Avoid direct exposure to sunlight. Styrolux® can be stored in silos at temperatures well below 45 °C.

PRODUCT SAFETY

During processing of Styrolux® small quantities of styrene monomer may be released into the atmosphere. At styrene vapor concentrations below 20 ppm no negative effects on health are expected. In our experience, the concentration of styrene does not exceed 1 ppm in well ventilated workplaces - that is where five to eight air changes per hour are made. For safety information please refer to our Material Safety Data Sheet for this product.

DISCLAIMER

The above information is provided in good faith. INEOS Styrolution is not responsible for any processing or compounding which may occur to product finished articles, packaging materials or their components. Further, INEOS Styrolution **MAKES NO WARRANTY OR REPRESENTATION OF ANY KIND, REGARDING THE INFORMATION GIVEN OR THE PRODUCTS DESCRIBED, AND EXPRESSLY DISCLAIMS ALL IMPLIED WARRANTIES, REPRESENTATIONS AND CONDITIONS, INCLUDING WITHOUT LIMITATION ALL WARRANTIES AND CONDITIONS OF QUALITY, MERCHANTABILITY AND SUITABILITY OR FITNESS FOR A PARTICULAR PURPOSE.** Responsibility for use, storage, handling and disposal of the products described herein is that of the purchaser or end user.
