

# Vydyne® 67B

## polyamide 66



Vydyne 67B is a very-high-viscosity PA66 resin suitable for injection-molding and extrusion applications. It is available in natural color only. Vydyne 67B resin offers high strength, rigidity and toughness over a broad range of demanding applications and good fluid resistance to a wide variety of chemicals, solvents and oils.

Typical Applications/End Uses:  
 Typical uses include packaging films, monofilaments, bristles, rods, tubing, sheet and extruded profiles.

General				
Material Status	• Commercial: Active			
Availability	• Asia Pacific	• Europe	• North America	
Features	• Gasoline Resistance • General Purpose • Good Chemical Resistance • Good Toughness	• High Melt Stability • High Rigidity • High Strength • High Viscosity	• Oil Resistant • Solvent Resistant	
Uses	• Film • Industrial Applications • Monofilaments	• Profiles • Rods • Sheet	• Tubing	
Agency Ratings	• ASTM D 4066 PA0114	• ASTM D 6779 PA0114	• FDA 21 CFR 177.1500	
RoHS Compliance	• RoHS Compliant			
Appearance	• Natural Color			
Forms	• Pellets			
Processing Method	• Extrusion			

Physical	Dry	Conditioned	Unit	Test Method
Density	1.14	--	g/cm <sup>3</sup>	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow : 73°F, 0.0787 in	2.1	--	%	
Flow : 73°F, 0.0787 in	2.2	--	%	
Water Absorption (Saturation, 73°F)	8.5	--	%	ISO 62
Water Absorption (Equilibrium, 73°F, 50% RH)	2.5	--	%	ISO 62

Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (73°F)	413000	276000	psi	ISO 527-2
Tensile Stress (Yield, 73°F)	12300	7980	psi	ISO 527-2
Tensile Stress (Break, 73°F)	7980	10200	psi	ISO 527-2
Tensile Strain (Yield, 73°F)	5.0	20	%	ISO 527-2
Nominal Tensile Strain at Break (73°F)	40	250	%	ISO 527-2
Flexural Modulus (73°F)	348000	109000	psi	ISO 178
Flexural Strength (73°F)	11600	2900	psi	ISO 178
Poisson's Ratio	0.40	--		ISO 527-2

© 2015 Ascend Performance Materials Operations LLC. The Ascend Performance Materials and Vydyne marks and logos are trademarks of Ascend Performance Materials Operations LLC. These trademarks have been registered in jurisdictions throughout the world, including the United States of America and the European Community.

Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-22°F	2.9	2.9	ft·lb/in <sup>2</sup>	
73°F	3.3	14	ft·lb/in <sup>2</sup>	
Charpy Unnotched Impact Strength				ISO 179/1eU
-22°F	No Break	No Break		
73°F	No Break	No Break		
Notched Izod Impact Strength				ISO 180
-22°F	2.9	2.9	ft·lb/in <sup>2</sup>	
73°F	3.3	14	ft·lb/in <sup>2</sup>	
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				ISO 75-2/B
66 psi, Unannealed	392	--	°F	
Heat Deflection Temperature				ISO 75-2/A
264 psi, Unannealed	149	--	°F	
Melting Temperature	500	--	°F	ISO 11357-3
CLTE - Flow (73 to 131°F, 0.0787 in)	5.6E-5	--	in/in/°F	ISO 11359-2
CLTE - Transverse (73 to 131°F, 0.0787 in)	5.6E-5	--	in/in/°F	ISO 11359-2
Extrusion	Dry Unit			
Cylinder Zone 1 Temp.	482 to 563 °F			
Cylinder Zone 2 Temp.	482 to 563 °F			
Cylinder Zone 3 Temp.	482 to 563 °F			
Cylinder Zone 4 Temp.	482 to 563 °F			
Cylinder Zone 5 Temp.	482 to 563 °F			
Melt Temperature	518 to 563 °F			
Die Temperature	518 to 563 °F			

#### Extrusion Notes

Recommended Extrusion Conditions:

Melt Point: 260°C

Melt Pressure: 3 to 17 MPa

Blow Film Bath Temperature: 20°C to 80°C

Chill Roll Temperature (Cast Film): 20°C to 80°C

Screw Design: General Purpose or Barrier

## Notes

Typical properties: these are not to be construed as specifications.

<sup>1</sup> Typical properties: these are not to be construed as specifications.



### North America

+1 888 927 2363

### Europe

+32 10 608 600

### Asia

+86 21 6340 3300

## Disclaimer of Warranty and Liability

NOTICE: Although the information and recommendations set forth herein (hereinafter "information") are presented in good faith and believed to be correct as of the date hereof, Ascend Performance Materials Operations LLC makes no representations or warranties as to the completeness or accuracy thereof.

Information is supplied upon the condition that the persons receiving same will make their own determination as to its suitability for their purposes prior to use. In no event will Ascend Performance Materials Operations LLC be responsible for damages of any nature whatsoever resulting from the use of or reliance upon information or the products to which information refers. Nothing contained herein is to be construed as a recommendation to use any product, equipment or formulation in conflict with any patent, and Ascend Performance Materials Operations LLC makes no representation or warranty, express or implied, that use thereof will not infringe any patent. No representations or warranties, either express or implied, of merchantability, fitness for a particular purpose or of any other nature are made hereunder with respect to information or the product to which information refers.