

# Vydyne® R530 NAT

## polyamide 66



Vydyne R530 NAT is general-purpose, injection-molding grade, 30% glass-fiber reinforced PA66 resin. Available in natural, it is lubricated for good machine feed, flow and mold release.

Typical Applications/End Uses:  
To come

General	
Material Status	• Commercial: Active
Availability	• Asia Pacific • Europe • North America
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight
Additive	• Lubricant
Features	• Antifreeze Resistant • Good Chemical Resistance • Hydrolysis Resistant • Fatigue Resistant • Good Flow • Lubricated • Gasoline Resistance • Heat Stabilized • Solvent Resistant
Uses	• Automotive Under the Hood
Agency Ratings	• ASTM D 4066 PA0111G30 • ASTM D 6779 PA0111G30
Automotive Specifications	• CHRYSLER MS-DB-41 CPN4018 • FORD WSK-M4D752-A • DAEWOO EDS-M-5164-11 • GM GMP.PA66.040 • OPEL QK 003013 HW • FORD WSK-M4D642-A • GM • TagAZ TAMS-8723-01 • FORD WSK-M4D642-A2 • GMW3038P-PA66-GF30H • OPEL QK 003013 H
UL File Number	• E70062
Appearance	• Natural Color
Forms	• Pellets
Processing Method	• Injection Molding

Physical	Dry	Conditioned	Unit	Test Method
Density	1.37	--	g/cm <sup>3</sup>	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow : 73°F, 0.0787 in	0.90	--	%	
Flow : 73°F, 0.0787 in	0.40	--	%	
Water Absorption (73°F, 24 hr)	0.90	--	%	ISO 62
Water Absorption (Equilibrium, 73°F, 50% RH)	1.9	--	%	ISO 62
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (73°F)	1.45E+6	1.07E+6	psi	ISO 527-2
Tensile Stress (Break, 73°F)	28300	19600	psi	ISO 527-2
Tensile Strain (Break, 73°F)	3.0	5.0	%	ISO 527-2
Flexural Modulus (73°F)	1.39E+6	870000	psi	ISO 178
Flexural Stress (73°F)	39200	27600	psi	ISO 178
Poisson's Ratio (73°F)	0.40	--		ISO 527

© 2015 Ascend Performance Materials Operations LLC. The Ascend Performance Materials and Vydyne marks and logos are trademarks of Ascend Performance Materials Operations LLC. These trademarks have been registered in jurisdictions throughout the world, including the United States of America and the European Community.

Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179
-22°F	4.9	5.2	ft·lb/in <sup>2</sup>	
73°F	5.3	6.2	ft·lb/in <sup>2</sup>	
Charpy Unnotched Impact Strength				ISO 179
-22°F	31	38	ft·lb/in <sup>2</sup>	
73°F	36	40	ft·lb/in <sup>2</sup>	
Notched Izod Impact Strength				ISO 180
-22°F	4.8	5.2	ft·lb/in <sup>2</sup>	
73°F	5.7	6.2	ft·lb/in <sup>2</sup>	
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				ISO 75-2/B
66 psi, Unannealed	500	--	°F	
Heat Deflection Temperature				ISO 75-2/A
264 psi, Unannealed	482	--	°F	
Melting Temperature	500	--	°F	ISO 11357-3
CLTE - Flow (73 to 131°F, 0.0787 in)	1.2E-5	--	in/in/°F	ISO 11359-2
CLTE - Transverse (73 to 131°F, 0.0787 in)	5.9E-5	--	in/in/°F	ISO 11359-2
RTI Elec				UL 746
0.0295 in	248	--	°F	
0.0591 in	248	--	°F	
0.118 in	248	--	°F	
RTI Imp				UL 746
0.0295 in	185	--	°F	
0.0591 in	185	--	°F	
0.118 in	221	--	°F	
RTI Str				UL 746
0.0295 in	239	--	°F	
0.0591 in	248	--	°F	
0.118 in	248	--	°F	

Electrical	Dry	Conditioned	Unit	Test Method
Volume Resistivity (0.118 in)	1.0E+14	--	ohm·cm	IEC 60093
Dielectric Strength (0.0394 in)	610	--	V/mil	IEC 60243
Arc Resistance (0.118 in)	PLC 5	--		ASTM D495
Comparative Tracking Index (0.118 in)	600	--	V	IEC 60112
High Amp Arc Ignition (HAI)				UL 746
0.0295 in	PLC 0	--		
0.0591 in	PLC 0	--		
0.118 in	PLC 0	--		
High Voltage Arc Tracking Rate (HVTR)	PLC 1	--		UL 746
Hot-wire Ignition (HWI)				UL 746
0.0295 in	PLC 4	--		
0.0591 in	PLC 4	--		
0.118 in	PLC 4	--		
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
0.0295 in	HB	--		
0.0591 in	HB	--		
0.118 in	HB	--		
Injection			Dry Unit	
Drying Temperature			176 °F	
Drying Time			4.0 hr	
Suggested Max Regrind			25 %	
Rear Temperature			536 to 590 °F	
Middle Temperature			536 to 590 °F	
Front Temperature			536 to 590 °F	
Nozzle Temperature			536 to 590 °F	
Processing (Melt) Temp			545 to 581 °F	
Mold Temperature			149 to 203 °F	

## Notes

Typical properties: these are not to be construed as specifications.

<sup>1</sup> Typical properties: these are not to be construed as specifications.



### North America

+1 888 927 2363

### Europe

+32 10 608 600

### Asia

+86 21 6340 3300

## Disclaimer of Warranty and Liability

NOTICE: Although the information and recommendations set forth herein (hereinafter "information") are presented in good faith and believed to be correct as of the date hereof, Ascend Performance Materials Operations LLC makes no representations or warranties as to the completeness or accuracy thereof.

Information is supplied upon the condition that the persons receiving same will make their own determination as to its suitability for their purposes prior to use. In no event will Ascend Performance Materials Operations LLC be responsible for damages of any nature whatsoever resulting from the use of or reliance upon information or the products to which information refers. Nothing contained herein is to be construed as a recommendation to use any product, equipment or formulation in conflict with any patent, and Ascend Performance Materials Operations LLC makes no representation or warranty, express or implied, that use thereof will not infringe any patent. No representations or warranties, either express or implied, of merchantability, fitness for a particular purpose or of any other nature are made hereunder with respect to information or the product to which information refers.