

# Chemlon® 220 G

Teknor Apex Company (Chem Polymer) - Polyamide 6

Tuesday, December 19, 2017

## General Information

### General

Material Status	• Commercial: Active		
Availability	• Asia Pacific	• Europe	• North America
Filler / Reinforcement	• Glass Fiber, 20% Filler by Weight		
Features	• Good Processability	• Good Toughness	• High Strength
Appearance	• Natural Color		
Forms	• Pellets		
Processing Method	• Injection Molding		

## ASTM & ISO Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.33		ASTM D792
Molding Shrinkage - Flow	5.0E-3	in/in	ASTM D955
Water Absorption (24 hr)	1.2	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	19000	psi	ASTM D638
Tensile Elongation (Yield)	3.5	%	ASTM D638
Flexural Modulus	825000	psi	ASTM D790
Flexural Strength (Yield)	28000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F)	1.7	ft-lb/in	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load 264 psi, Unannealed	400	°F	ASTM D648
Melting Temperature	420	°F	

## Processing Information

Injection	Nominal Value	Unit
Drying Temperature	150 to 180	°F
Suggested Max Moisture	0.20	%
Rear Temperature	520	°F
Middle Temperature	510	°F
Front Temperature	480	°F
Nozzle Temperature	480	°F
Mold Temperature	140 to 200	°F
Injection Pressure	5000 to 20000	psi
Screw Speed	60 to 120	rpm

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

Revision Date: 12/11/2008

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

# Chemlon® 220 G

## Teknor Apex Company (Chem Polymer) - Polyamide 6

### Teknor Apex Company Corporate Headquarters

*In U.S. for Vinyls, TPEs, Colorants,  
Engineered Thermoplastics (Chem Polymer)*  
505 Central Avenue  
Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000  
Fax: 401-725-8095  
Toll Free (U.S. only) 800-556-3864

[www.teknorapex.com](http://www.teknorapex.com)  
[info@teknorapex.com](mailto:info@teknorapex.com)

### Teknor Apex U.K. Ltd.

Tat Bank Road  
Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100  
Fax: (44) 121-544-5530

[www.teknorapex.com](http://www.teknorapex.com)  
[etpsales@teknorapex.co.uk](mailto:etpsales@teknorapex.co.uk)

### Teknor Apex (Suzhou) Advanced Polymer Compounds Co. Pte. Ltd.

No. 78 Ping Sheng Road  
Suzhou Industrial Park  
Jiangsu, China 215126

Phone: (86) 512-6287-1550  
Fax: (86) 512-6288-8371

[www.teknorapex.com](http://www.teknorapex.com)  
[infotaap@teknorapex.com](mailto:infotaap@teknorapex.com)

### Teknor Apex Asia Pacific PTE. LTD.

41 Shipyard Road  
Singapore 628134

Phone: (65) 6265-2544  
Fax: (65) 6265-1821

[www.teknorapex.com](http://www.teknorapex.com)  
[infotaap@teknorapex.com](mailto:infotaap@teknorapex.com)

Revision Date: 12/11/2008

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.