

# Chemlon® 235G

Teknor Apex Company (Chem Polymer) - Polyamide 6

Tuesday, December 19, 2017

## General Information

### Product Description

235G is a 35% glass fibre reinforced nylon 6 that offers a balance between mechanical performance, surface finish and mould release characteristics.

### General

Material Status	• Commercial: Active
Availability	• Europe
Filler / Reinforcement	• Glass Fiber, 35% Filler by Weight
Processing Method	• Injection Molding

## ASTM & ISO Properties <sup>1</sup>

Physical	Dry	Conditioned	Unit	Test Method
Density	1.41	--	g/cm <sup>3</sup>	ISO 1183
Molding Shrinkage <sup>2</sup>	0.70 to 1.2	--	%	Internal Method
Water Absorption				ISO 62
Equilibrium, 73°F, 50% RH	1.9	--	%	
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	1.45E+6	1.16E+6	psi	ISO 527-2
Tensile Stress	26100	17400	psi	ISO 527-2
Tensile Strain (Break)	4.0	6.0	%	ISO 527-2
Flexural Modulus	1.33E+6	653000	psi	ISO 178
Flexural Stress	37700	20300	psi	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength	8.1	18	ft·lb/in <sup>2</sup>	ISO 179/1eA
Charpy Unnotched Impact Strength	26	--	ft·lb/in <sup>2</sup>	ISO 179/1eU
Notched Izod Impact Strength	6.7	--	ft·lb/in <sup>2</sup>	ISO 180/A
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				ISO 75-2/B
66 psi, Unannealed	> 392	--	°F	
Heat Deflection Temperature				ISO 75-2/A
264 psi, Unannealed	> 392	--	°F	
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	1.0E+14	1.0E+11	ohms	IEC 60093
Volume Resistivity	1.0E+16	1.0E+14	ohms·cm	IEC 60093
Electric Strength (0.118 in)	280	200	V/mil	IEC 60243-1
Relative Permittivity	3.80	4.20		IEC 60250
Comparative Tracking Index	500	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
0.06 in, Teknor Apex test result	HB	--		
Oxygen Index	24	--	%	ISO 4589-2

## Processing Information

Injection	Dry	Unit
Drying Temperature	176	°F
Drying Time	20	hr
Rear Temperature	482 to 536	°F

Revision Date: 3/17/2014

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

# Chemlon® 235G

## Teknor Apex Company (Chem Polymer) - Polyamide 6

Injection	Dry Unit
Middle Temperature	482 to 536 °F
Front Temperature	482 to 536 °F
Processing (Melt) Temp	482 to 554 °F
Mold Temperature	158 to 194 °F
Injection Rate	Fast
Back Pressure	Low
Screw Speed	Moderate

### Injection Notes

No drying is necessary unless the material has been exposed to air for longer than three hours. The appearance of splash marks on the surface of mouldings indicates excessive moisture is present.

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> Mould shrinkage is significantly influenced by many factors including wall thickness, gating, moulding shape and processing conditions. The range values given are determined from specimen bar mouldings of 1.5mm to 4mm wall thickness. They are provided as a guide for comparison purposes only and no guarantee should be inferred from their inclusion. (Specimens measured in the dry state, 24 hours after moulding).

#### Teknor Apex Company Corporate Headquarters

*In U.S. for Vinyls, TPEs, Colorants,  
Engineered Thermoplastics (Chem Polymer)*  
505 Central Avenue  
Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000  
Fax: 401-725-8095  
Toll Free (U.S. only) 800-556-3864

[www.teknorapex.com](http://www.teknorapex.com)  
[info@teknorapex.com](mailto:info@teknorapex.com)

#### Teknor Apex U.K. Ltd.

Tat Bank Road  
Oldbury, West Midlands B69 4NH England

Phone: (44) 121-665-2100  
Fax: (44) 121-544-5530

[www.teknorapex.com](http://www.teknorapex.com)  
[etpsales@teknorapex.co.uk](mailto:etpsales@teknorapex.co.uk)

#### Teknor Apex (Suzhou) Advanced Polymer Compounds Co. Pte. Ltd.

No. 78 Ping Sheng Road  
Suzhou Industrial Park  
Jiangsu, China 215126

Phone: (86) 512-6287-1550  
Fax: (86) 512-6288-8371

[www.teknorapex.com](http://www.teknorapex.com)  
[infotaap@teknorapex.com](mailto:infotaap@teknorapex.com)

#### Teknor Apex Asia Pacific PTE. LTD.

41 Shipyard Road  
Singapore 628134

Phone: (65) 6265-2544  
Fax: (65) 6265-1821

[www.teknorapex.com](http://www.teknorapex.com)  
[infotaap@teknorapex.com](mailto:infotaap@teknorapex.com)

Revision Date: 3/17/2014

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.