

K-Resin KK38

Styrene Butadiene Copolymer (SBC)

TECHNICAL DATASHEET

DESCRIPTION

K-Resin® KK38 alone or in blends, can be extruded into sheet and thermoformed on conventional equipment at high output rates. The favorable economics of K-Resin® SBC, along with high productivity, have made possible tough clear disposable drinking cups, lids and other packaging applications. INEOS Styrolution has several grades of K-Resin® SBC tailored for your sheet extrusion needs.

FEATURES

- Combines Clarity and Toughness
- Good Formability
- High Surface Gloss
- Good Toughness and Stiffness

APPLICATIONS

- Thermoformed Blister Packs
- Portion Packages
- Cups and Lids

Property, Test Condition	Standard	Unit	Values
Rheological Properties			
Melt Flow Rate, 200 °C/5 kg	ASTM D 1238	g/10 min	9.0
Mechanical Properties			
Instrumented Dart Impact (total energy)	ASTM D 3763	in-lbs	340
Tensile Stress at Yield, 23 °C	ASTM D 638	psi	2,350
Tensile Strain at Break, 23 °C	ASTM D 638	%	260
Flexural Strength, 23 °C	ASTM D 790	psi	3,600
Flexural Modulus, 23 °C	ASTM D 790	psi x 10 ³	198,000
Hardness, Shore D	ASTM D 2240	-	56
Thermal Properties			
Vicat Softening Temperature, B/1 (120 °C/h, 10N)	ASTM D 1525	°F	166
DTUL @ 264 psi - Annealed	ASTM D 648	°F	134
Optical Properties			
Light Transmission at 550 nm	ASTM D 1003	%	92
Other Properties			
Density	ASTM D 792	-	1.00

The nominal properties herein are typical of the product but do not reflect normal testing variance and therefore should not be used for specification

K-Resin KK38

Styrene Butadiene Copolymer (SBC)

TECHNICAL DATASHEET

purposes. Values are rounded.

[Tensile Yield Strength/Tensile Yield Strength] = Type 1 @ 2 in/min (50 mm/min)

[Flexural Modulus/Flexural Yield Strength] = 0.125 in (3.2 mm) specimen @ 0.5 in/sec (1.27 cm/min)

[Instrumented Dart Impact] = Total Energy 3.2 mm, 381 cm/s, 12.7 mm tup

DISCLAIMER

The above information is provided in good faith. INEOS Styrolution is not responsible for any processing or compounding which may occur to product finished articles, packaging materials or their components. Further, INEOS Styrolution MAKES NO WARRANTY OR REPRESENTATION OF ANY KIND, REGARDING THE INFORMATION GIVEN OR THE PRODUCTS DESCRIBED, AND EXPRESSLY DISCLAIMS ALL IMPLIED WARRANTIES, REPRESENTATIONS AND CONDITIONS, INCLUDING WITHOUT LIMITATION ALL WARRANTIES AND CONDITIONS OF QUALITY, MERCHANTABILITY AND SUITABILITY OR FITNESS FOR A PARTICULAR PURPOSE. Responsibility for use, storage, handling and disposal of the products described herein is that of the purchaser or end user.
