

# Vydyne® 41H NT

## polyamide 66



Vydyne 41H NT is general-purpose, impact-modified PA66 resin. Available in natural, it is heat-stabilized for improved resistance to elevated temperatures. The heat stabilization package for Vydyne 41H NT was formulated to provide thermal endurance when used in applications in which continuous or extended high-temperature exposure is anticipated.

Vydyne 41H NT is recognized for all the processing and property advantages inherent to PA66 with the addition of improved impact

strength. This resin offers a well balanced combination of engineering properties characterized by high melt point, good surface lubricity, abrasion resistance and resistance to many chemicals, machine and motor oils, solvents and gasoline.

Typical Applications/End Uses:

Vydyne 41H NT is designed to meet the critical low-temperature impact requirements called out in many automotive specifications.

General				
Material Status	• Commercial: Active			
Availability	• Asia Pacific	• Europe	• North America	
Additive	• Impact Modifier			
Features	• Gasoline Resistance • Good Abrasion Resistance • Good Chemical Resistance	• Good Processability • High Impact Resistance • Impact Modified	• Low Temperature Impact Resistance • Oil Resistant • Solvent Resistant	
Uses	• Automotive Applications • Connectors • Consumer Applications	• Electrical/Electronic Applications • Fasteners • Gears	• Industrial Applications	
Agency Ratings	• ASTM D 4066 PA0181	• ASTM D 6779 PA0181		
Appearance	• Natural Color			
Forms	• Pellets			
Processing Method	• Injection Molding			
Physical	Dry	Conditioned	Unit	Test Method
Density	1.08	--	g/cm <sup>3</sup>	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow : 0.0787 in	1.6	--	%	
Flow : 0.0787 in	1.8	--	%	
Water Absorption (73°F, 24 hr)	1.0	--	%	ISO 62
Water Absorption (Equilibrium, 73°F, 50% RH)	2.1	--	%	ISO 62
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (73°F)	270000	201000	psi	ISO 527-2
Tensile Stress (Yield, 73°F)	7250	5080	psi	ISO 527-2
Tensile Stress (Break, 73°F)	6240	5660	psi	ISO 527-2
Tensile Strain (Break, 73°F)	50	180	%	ISO 527-2
Flexural Modulus (73°F)	254000	79000	psi	ISO 178
Flexural Stress (73°F)	7690	2470	psi	ISO 178

Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179
-40°F	9.5	12	ft·lb/in <sup>2</sup>	
-22°F	17	12	ft·lb/in <sup>2</sup>	
73°F	36	53	ft·lb/in <sup>2</sup>	
Charpy Unnotched Impact Strength				ISO 179
-22°F	No Break	No Break		
73°F	No Break	No Break		
Notched Izod Impact Strength				ISO 180
-40°F	10	12	ft·lb/in <sup>2</sup>	
-22°F	19	14	ft·lb/in <sup>2</sup>	
73°F	37	42	ft·lb/in <sup>2</sup>	
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				ISO 75-2/B
66 psi, Unannealed	293	--	°F	
Heat Deflection Temperature				ISO 75-2/A
264 psi, Unannealed	136	--	°F	
Melting Temperature	500	--	°F	ISO 11357-3
CLTE - Flow (73 to 131°F, 0.0787 in)	9.3E-5	--	in/in/°F	ISO 11359-2
CLTE - Transverse (73 to 131°F, 0.0787 in)	8.3E-5	--	in/in/°F	ISO 11359-2
RTI Elec				UL 746
0.0295 in	266	--	°F	
0.0591 in	266	--	°F	
0.118 in	266	--	°F	
RTI Imp				UL 746
0.0295 in	167	--	°F	
0.0591 in	167	--	°F	
0.118 in	167	--	°F	
RTI Str				UL 746
0.0295 in	239	--	°F	
0.0591 in	248	--	°F	
0.118 in	257	--	°F	

Electrical	Dry	Conditioned	Unit	Test Method
Volume Resistivity (0.0295 in)	1.0E+10	--	ohm-cm	IEC 60093
Dielectric Strength (0.0394 in)	360	--	V/mil	IEC 60243
Arc Resistance (0.118 in)	PLC 6	--		ASTM D495
Comparative Tracking Index (0.118 in)	600	--	V	IEC 60112
High Amp Arc Ignition (HAI)				UL 746
0.0295 in	PLC 0	--		
0.0591 in	PLC 0	--		
0.118 in	PLC 0	--		
High Voltage Arc Tracking Rate (HVTR)	PLC 2	--		UL 746
Hot-wire Ignition (HWI)				UL 746
0.0295 in	PLC 4	--		
0.0591 in	PLC 4	--		
0.118 in	PLC 3	--		
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
0.0295 in	HB	--		
0.0591 in	HB	--		
0.118 in	HB	--		
Glow Wire Flammability Index				IEC 60695-2-12
0.0295 in	1340	--	°F	
0.0591 in	1340	--	°F	
0.118 in	1250	--	°F	
Glow Wire Ignition Temperature				IEC 60695-2-13
0.0295 in	1380	--	°F	
0.0591 in	1380	--	°F	
0.118 in	1290	--	°F	
Injection		Dry	Unit	
Drying Temperature		176	°F	
Drying Time		4.0	hr	
Suggested Max Regrind		25	%	
Rear Temperature		536 to 590	°F	
Middle Temperature		536 to 590	°F	
Front Temperature		536 to 590	°F	
Nozzle Temperature		536 to 590	°F	
Processing (Melt) Temp		545 to 581	°F	
Mold Temperature		149 to 203	°F	

## Notes

Typical properties: these are not to be construed as specifications.

<sup>1</sup> Typical properties: these are not to be construed as specifications.



### North America

+1 888 927 2363

### Europe

+32 10 608 600

### Asia

+86 21 6340 3300

## Disclaimer of Warranty and Liability

NOTICE: Although the information and recommendations set forth herein (hereinafter "information") are presented in good faith and believed to be correct as of the date hereof, Ascend Performance Materials Operations LLC makes no representations or warranties as to the completeness or accuracy thereof.

Information is supplied upon the condition that the persons receiving same will make their own determination as to its suitability for their purposes prior to use. In no event will Ascend Performance Materials Operations LLC be responsible for damages of any nature whatsoever resulting from the use of or reliance upon information or the products to which information refers. Nothing contained herein is to be construed as a recommendation to use any product, equipment or formulation in conflict with any patent, and Ascend Performance Materials Operations LLC makes no representation or warranty, express or implied, that use thereof will not infringe any patent. No representations or warranties, either express or implied, of merchantability, fitness for a particular purpose or of any other nature are made hereunder with respect to information or the product to which information refers.