

# Vydyne® M344 BLK

## polyamide 66



Vydyne M344 BLK is an halogenated, unfilled, flame-retardant PA66/6 copolymer designed with excellent strength and toughness. It is lubricated for machine feed and easy mold release

and has an Underwriters Laboratories UL 94 flammability classification of V-0 at 0.4 mm (0.016") thick.

General				
Material Status	• Commercial: Active			
Availability	• Asia Pacific	• Europe	• North America	
Additive	• Halogen	• Lubricant		
Features	• Ductile • Good Mold Release	• Halogenated • Ignition Resistant	• Low Density • Lubricated	
Uses	• Appliances • Automotive Electronics • Bobbins • Connectors • Electrical Housing	• Electrical Parts • Electrical/Electronic Applications • Fasteners • Industrial Applications • Lighting Applications	• Living Hinges • Printed Circuit Boards • Switches	
UL File Number	• E70062			
Appearance	• Black			
Forms	• Pellets			
Processing Method	• Injection Molding			
Physical	Dry	Conditioned	Unit	Test Method
Density	1.27	--	g/cm <sup>3</sup>	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow : 73°F, 0.0787 in	1.8	--	%	
Flow : 73°F, 0.0787 in	1.3	--	%	
Water Absorption (73°F, 24 hr)	0.80	--	%	ISO 62
Water Absorption (Equilibrium, 73°F, 50% RH)	1.9	--	%	ISO 62
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (73°F)	508000	334000	psi	ISO 527-2
Tensile Stress (Yield, 73°F)	8700	5800	psi	ISO 527-2
Tensile Strain (Yield, 73°F)	5.2	25	%	ISO 527-2
Tensile Strain (Break, 73°F)	35	75	%	ISO 527-2
Flexural Modulus (73°F)	435000	203000	psi	ISO 178
Flexural Strength (73°F)	13100	6240	psi	ISO 178
Poisson's Ratio	0.40	--		ISO 527-2

Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-22°F	2.5	--	ft·lb/in <sup>2</sup>	
73°F	2.6	--	ft·lb/in <sup>2</sup>	
Charpy Unnotched Impact Strength				ISO 179/1eU
-22°F	No Break	--		
73°F	No Break	--		
Notched Izod Impact Strength (73°F)	2.4	--	ft·lb/in <sup>2</sup>	ISO 180
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				ISO 75-2/B
66 psi, Unannealed	367	--	°F	
Heat Deflection Temperature				ISO 75-2/A
264 psi, Unannealed	149	--	°F	
Melting Temperature (DSC)	482	--	°F	ISO 3146
CLTE - Flow (73 to 131°F, 0.0787 in)	5.6E-5	--	in/in/°F	ISO 11359-2
CLTE - Transverse (73 to 131°F, 0.0787 in)	5.6E-5	--	in/in/°F	ISO 11359-2
RTI Elec				UL 746
0.0157 in	149	--	°F	
0.0295 in	266	--	°F	
0.0591 in	266	--	°F	
0.118 in	266	--	°F	
RTI Imp				UL 746
0.0157 in	149	--	°F	
0.0295 in	149	--	°F	
0.0591 in	203	--	°F	
0.118 in	203	--	°F	
RTI Str				UL 746
0.0157 in	149	--	°F	
0.0295 in	203	--	°F	
0.0591 in	203	--	°F	
0.118 in	203	--	°F	

Electrical	Dry	Conditioned	Unit	Test Method
Volume Resistivity (0.0295 in)	1.0E+10	--	ohm-cm	IEC 60093
Dielectric Strength (0.0394 in)	660	--	V/mil	IEC 60243
Arc Resistance (0.118 in)	PLC 6	--		ASTM D495
Comparative Tracking Index (0.118 in)	400 to 599	--	V	IEC 60112
High Amp Arc Ignition (HAI)				UL 746
0.0295 in	PLC 0	--		
0.0591 in	PLC 0	--		
0.118 in	PLC 0	--		
High Voltage Arc Tracking Rate (HVTR)	PLC 1	--		UL 746
Hot-wire Ignition (HWI)				UL 746
0.0295 in	PLC 0	--		
0.0591 in	PLC 0	--		
0.118 in	PLC 0	--		
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
0.0157 in	V-0	--		
0.0295 in	V-0	--		
0.0591 in	V-0	--		
0.118 in	V-0	--		
Glow Wire Flammability Index				IEC 60695-2-12
0.0295 in	1760	--	°F	
0.0591 in	1760	--	°F	
0.118 in	1760	--	°F	
Glow Wire Ignition Temperature				IEC 60695-2-13
0.0295 in	1290	--	°F	
0.0591 in	1290	--	°F	
0.118 in	1340	--	°F	
Oxygen Index	30	--	%	ISO 4589-2

Injection	Dry Unit
Drying Temperature	176 °F
Drying Time	4.0 hr
Suggested Max Regrind	25 %
Rear Temperature	464 to 518 °F
Middle Temperature	464 to 518 °F
Front Temperature	464 to 518 °F
Nozzle Temperature	464 to 518 °F
Processing (Melt) Temp	482 to 518 °F
Mold Temperature	149 to 203 °F

**Notes**

Typical properties: these are not to be construed as specifications.

<sup>1</sup> Typical properties: these are not to be construed as specifications.



**North America**  
+1 888 927 2363

**Europe**  
+32 10 608 600

**Asia**  
+86 21 6340 3300

**Disclaimer of Warranty and Liability**

NOTICE: Although the information and recommendations set forth herein (hereinafter "information") are presented in good faith and believed to be correct as of the date hereof, Ascend Performance Materials Operations LLC makes no representations or warranties as to the completeness or accuracy thereof.

Information is supplied upon the condition that the persons receiving same will make their own determination as to its suitability for their purposes prior to use. In no event will Ascend Performance Materials Operations LLC be responsible for damages of any nature whatsoever resulting from the use of or reliance upon information or the products to which information refers. Nothing contained herein is to be construed as a recommendation to use any product, equipment or formulation in conflict with any patent, and Ascend Performance Materials Operations LLC makes no representation or warranty, express or implied, that use thereof will not infringe any patent. No representations or warranties, either express or implied, of merchantability, fitness for a particular purpose or of any other nature are made hereunder with respect to information or the product to which information refers.