

Vydyne® 20NSP BLK

polyamide 66



Vydyne 20NSP BLK is a general-purpose, highly nucleated, lubricated PA66 resin. Available in black, it is designed to crystallize rapidly in order to reduce cycle times and increase productivity through faster part set-up. The higher crystalline structure will increase tensile modulus and strength, reduce elongation and may slightly lower mold shrinkage when compared to standard general-purpose non nucleated PA66. The rapid crystallization of Vydyne 20NSP BLK resin may allow part ejection at a higher temperature compared to general-purpose PA66. Critical factors unique to each application such as mold design, part design, tolerances and other factors will dictate ultimate cycle

time benefits. It is recommended to check critical part dimensions against specifications before adopting shorter molding cycles. Vydyne 20NSP BLK resin has an external lubricant for improved machine feed and an internal lubricant for improved mold release.

Typical Applications/End Uses:

End uses for Vydyne 20NSP BLK include terminal blocks, bearings, control cams, electrical connectors, housings, cable ties, fasteners, switch components and industrial parts that require chemical resistance, stiffness, wear resistance and rigidity.

General				
Material Status	• Commercial: Active			
Availability	• Asia Pacific	• Europe	• North America	
Additive	• Lubricant	• Nucleating Agent		
Features	• Fast Molding Cycle • General Purpose • Good Mold Release	• Good Stiffness • High Rigidity • Lubricated	• Nucleated	
Uses	• Bearings • Cams • Connectors	• Fasteners • General Purpose • Housings	• Industrial Applications	
Agency Ratings	• ASTM D 4066 PA0131	• ASTM D 6779 PA0131	• FED L-P-410A	
RoHS Compliance	• RoHS Compliant			
Automotive Specifications	• ASTM D4000 PA131	• ASTM D4066 PA0131	• FEDERAL LP410A	
UL File Number	• E70062			
Appearance	• Black			
Forms	• Pellets			
Processing Method	• Injection Molding			
Physical	Dry	Conditioned	Unit	Test Method
Density	1.14	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow : 73°F, 0.0787 in	1.6	--	%	
Flow : 73°F, 0.0787 in	1.4	--	%	
Water Absorption (73°F, 24 hr)	1.2	--	%	ISO 62
Water Absorption (Equilibrium, 73°F, 50% RH)	2.4	--	%	ISO 62

Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (73°F)	551000	363000	psi	ISO 527-2
Tensile Stress (Yield, 73°F)	13800	8700	psi	ISO 527-2
Tensile Stress (Break, 73°F)	10900	7250	psi	ISO 527-2
Tensile Strain (Yield, 73°F)	5.0	15	%	ISO 527-2
Nominal Tensile Strain at Break (73°F)	13	20	%	ISO 527-2
Flexural Modulus (73°F)	464000	189000	psi	ISO 178
Flexural Strength (73°F)	14500	5080	psi	ISO 178
Poisson's Ratio	0.40	--		ISO 527-2
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-22°F	2.4	2.4	ft·lb/in ²	
73°F	2.9	7.1	ft·lb/in ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-22°F	No Break	No Break		
73°F	No Break	No Break		
Notched Izod Impact Strength				ISO 180
-22°F	2.4	2.4	ft·lb/in ²	
73°F	2.9	7.1	ft·lb/in ²	

Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature 66 psi, Unannealed	446	--	°F	ISO 75-2/B
Heat Deflection Temperature 264 psi, Unannealed	194	--	°F	ISO 75-2/A
Melting Temperature	500	--	°F	ISO 11357-3
CLTE - Flow (73 to 131°F, 0.0787 in)	5.6E-5	--	in/in/°F	ISO 11359-2
CLTE - Transverse (73 to 131°F, 0.0787 in)	5.6E-5	--	in/in/°F	ISO 11359-2
RTI Elec				UL 746
0.0157 in	266	--	°F	
0.0280 in	266	--	°F	
0.0591 in	266	--	°F	
0.118 in	266	--	°F	
RTI Imp				UL 746
0.0157 in	167	--	°F	
0.0280 in	167	--	°F	
0.0591 in	167	--	°F	
0.118 in	167	--	°F	
RTI Str				UL 746
0.0157 in	167	--	°F	
0.0280 in	185	--	°F	
0.0591 in	185	--	°F	
0.118 in	185	--	°F	
Electrical	Dry	Conditioned	Unit	Test Method
Volume Resistivity (0.0295 in)	1.0E+10	--	ohm·cm	IEC 60093
Dielectric Strength (0.0394 in)	660	--	V/mil	IEC 60243
Arc Resistance (0.118 in)	PLC 5	--		ASTM D495
Comparative Tracking Index (0.118 in)	600	--	V	IEC 60112
High Amp Arc Ignition (HAI)				UL 746
0.0280 in	PLC 0	--		
0.0591 in	PLC 0	--		
0.118 in	PLC 0	--		
High Voltage Arc Tracking Rate (HVTR)	PLC 0	--		UL 746
Hot-wire Ignition (HWI)				UL 746
0.0280 in	PLC 4	--		
0.0591 in	PLC 3	--		
0.118 in	PLC 3	--		

Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
0.0157 in	V-2	--		
0.0280 in	V-2	--		
0.0591 in	V-2	--		
0.118 in	V-2	--		
Glow Wire Flammability Index				IEC 60695-2-12
0.0280 in	1470	--	°F	
0.0591 in	1470	--	°F	
0.118 in	1710	--	°F	
Glow Wire Ignition Temperature				IEC 60695-2-13
0.0280 in	1290	--	°F	
0.0591 in	1290	--	°F	
0.118 in	1290	--	°F	
Oxygen Index	26	--	%	ISO 4589-2
Injection		Dry Unit		
Drying Temperature		< 158 °F		
Drying Time		1.0 to 3.0 hr		
Suggested Max Regrind		50 %		
Rear Temperature		500 to 536 °F		
Middle Temperature		518 to 545 °F		
Front Temperature		536 to 554 °F		
Nozzle Temperature		536 to 572 °F		
Processing (Melt) Temp		545 to 572 °F		
Mold Temperature		149 to 203 °F		

Notes

Typical properties: these are not to be construed as specifications.

¹ Typical properties: these are not to be construed as specifications.



North America

+1 888 927 2363

Europe

+32 10 608 600

Asia

+86 21 6340 3300

Disclaimer of Warranty and Liability

NOTICE: Although the information and recommendations set forth herein (hereinafter "information") are presented in good faith and believed to be correct as of the date hereof, Ascend Performance Materials Operations LLC makes no representations or warranties as to the completeness or accuracy thereof.

Information is supplied upon the condition that the persons receiving same will make their own determination as to its suitability for their purposes prior to use. In no event will Ascend Performance Materials Operations LLC be responsible for damages of any nature whatsoever resulting from the use of or reliance upon information or the products to which information refers. Nothing contained herein is to be construed as a recommendation to use any product, equipment or formulation in conflict with any patent, and Ascend Performance Materials Operations LLC makes no representation or warranty, express or implied, that use thereof will not infringe any patent. No representations or warranties, either express or implied, of merchantability, fitness for a particular purpose or of any other nature are made hereunder with respect to information or the product to which information refers.